













# TEST REPORT



SHENZHEN JIERUIJIA TRADING CO., LTD  
NO.415 RUNLIAN BUILDING, SHENZHU ROAD,  
HENGANG, 518115, SHENZHEN, CHINA

LAB LOCATION: SHENZHEN  
LAB NUMBER: 0521097-0435

ATTN: EMMA ZOU  
CC: emma@cupwind.com

DATE IN: APR 07, 2021  
MO. LOG IN: /  
DATE OUT: APR 13, 2021  
REVISED DATE: /  
WORKING DAYS: 5  
PAGE: 2 OF 4

OVERALL RATING	
PASS	X
FAIL	
DATA	

### TESTING FOR CA 95 LEAD & CADMIUM ON NON-FOOD BEVERAGE GLASSWARE-EXTERIOR

Sample Description:	IRIDESCENT COATING CANDLE JAR		
Manufacturer:	CUPWIND COOPERATED FACILITY	P.O. No.:	/
Buyer:	SPT	Style:	
Country of Origin:	CHINA	Country of Destination:	USA
Color:	IRIDESCENT	SKU Number:	ITEM: 8090
Brand name:	CUPWIND IS		
Re-test:	Yes: <input type="checkbox"/> No: <input checked="" type="checkbox"/>	Change Vendor:	Yes: <input type="checkbox"/> No: <input type="checkbox"/>
Previous Report No.:	/		

### EXECUTIVE SUMMARY:

Test content	Result/Pass	Result/Pass	Result/Pass	
CA 95 Lead & Cadmium on non-food/beverage glassware-exterior	Meet Pass			
Electrodeless of annealing	ASTM F2175-20 (Sec. 4.2.5A6)	With a larger particle size, scratch area around the inside knuckle of the article. Then scratch on "X" across the entire inside bottom surface of the article. All scratches are to be made using sufficient pressure to just penetrate the surface of the glass. Fill each article with water at the same room temperature as the glass. Wait 15 minutes, then empty the water and examine each piece for fractures. That show no fractures. Report the number of fractures, if any, for each test.	M	PASS
Thermal shock	ASTM F2175-20 (Sec. 4.2.5A6) / ASTM C149	Modification: expanded scope to all other glass products in addition to jar/candle containers. That not crack or break after tested per below: -prepare a cold water bath at 21± 1.1°C (70 ± 2°F); -immerse a hot bath at 71 ± 1.1°C (160 ± 2°F); -immerse the sample completely in the hot water bath and allow to soak for 5 min ± 15 s; -transfer the sample to the cold bath; and -immerse for at least 30 s; -remove the sample from the cold bath and examine the sample for any cracking. Note: -the hot water that collects within the container during the first immersion shall be retained in the container through the second immersion; -the time of transfer from the hot bath to the cold bath shall be 15 ± 1 s. Modification: sampling procedure not followed and expanded scope to all other glass products in addition to jar/candle containers.	M	PASS

### REMARK:

1. No enclosed protocol for test results in this report.

XXXXXXXXXXXXXXXXXXXX

XXXXXXXX Cupwind XXXXX XXXXXXX XXXXXXX XX XXXX XXX.

XX XXXX 144 / XXXX 72 / XXXX 48 / XXXX 24 XXXXX XXX X XXXXX XXXXXXXXXXX XXXX XXXX XXXX XX XXXXX XXX XXX XXXXX XX XXXXXXX XXXXX.

XXXX XXXX XX XXXXX XXXX XXXXX XXXXX X XXXXXXX XX X XXXXXXX XXXXXXX XXXX XXXXX XXXXX XXXXX XXXXX XXXXXXX XXXXXXX XX XXXXXXX XXXXX.



