□□□□□□ □□□□ □□□□□□ □□□□□ □□□□□ □□□□□□□ □□□□

□□□□□

□□□□ □□□ 10000 □□□□□ □□□□.

20 □□□□□□□□ □□□□□□□ □□□□ □□ □□□□.

20 □□□□□□□ □□□□ □□ □□□□□□ □□ □□□□.

20 □□□□ □□□□□ □□□□ □□□□.

□□□ □□□□ □□□□ □□□□□□□ □□□□□□□□ □□□□□□□□ Armani Zara □□□.

Cupwind □□□□□ □□ .

□□□□□ □□□□ Cupwind □□ ODM / OEM □ □□□ □□□□□□ □□□□□ □□□□ □□□□□□□ □□□□□□ □□□ □□□□□□ □ □□□□ □□□□□ □□□□□□□ □□□□□□ □□□□□□ □□□□□□□□ □□ □□□□□□ □□□□□□ □ □□□□ □□□□□□ □□ □□□ □□□□□ .□□□□□□ □□□□□ □□ □□□□□.

□□□□ Cupwind □□□□□ □□□□ □□□□ OEM □ ODM □□□□□□.

□□□□□□□ □□□□□□□□ □□□□□□□□ □□□□ □□□□□□ □□□□□□□ □□ □□□□□□ □□ □□□□□□ □□□.

□□□□□□□ □□□□□□ □□□□□ □□□ □□□□ □□□□□ □□□□ □□□□□.

Cupwind □ □□□□□□□ □□□□□□□ □□□□□□ □□□□ □□ .

TEST REPORT

SHENZHEN JIERUIMA TRADING CO., LTD.
NO.415 RUNLIAN BUILDING, SHENZHU ROAD,
HENGGANG, 518115, SHENZHEN, CHINA

LAB LOCATION: SHENZHEN
LAB NUMBER: (8521)097-0435

ATTN: EMMA ZOU
CC: emma@cupwind.com

DATE IN: APR 07, 2021
MOD. LOG IN: /
DATE OUT: APR 13, 2021
REVISED DATE: /
WORKING DAYS: 5
PAGE: 2 OF 4

OVERALL RATING

PASS	X
FAIL	
DATA	

TESTING FOR
CA 65 LEAD & CADMIUM ON NON-FOOD / BEVERAGE GLASSWARE-EXTERIOR

Sample Description:	IRIDESCENT COATING CANDLE JAR						
Manufacturer:	CUPWIND COOPERATED FACILITY		**P.O. No.:**	/			
Buyer:	IPSY		**Style:**	/			
Country of Origin:	CHINA		**Country of Destination:**	USA			
Color:	IRIDESCENT		**SKU Number:**	ITEM#: 8090			
Brand name:	CUPWIND IB						
Re-test:	Yes:	No: X	**Charge Vendor:**	Yes: X	No:		
Previous Report No.:	/						

(8521)097-0435
Page 3 of 4

EXECUTIVE SUMMARY:

Test content	Result/Rating
CA 65 Lead & Cadmium on non-food/beverage glassware-exterior	Meet/Pass

Effectiveness of annealing	ASTM F2179-20 Sec. 4.2 (Mod)	With a tungsten carbide scribe, scratch once around the inside knuckle of the article. Then scratch an "X" across the entire inside bottom surface of the article. All scratches are to be made using sufficient pressure to just penetrate the surface of the glass. Fill each article with water at the same room temperature as the glass. Wait 15 minutes, then empty the water and examine each piece for fractures. Shall show no fractures. Report the number of fractures, if any, for each test. Modification: expanded scope to all other glass products in addition to candle containers.	Id	PASS
Thermal shock	ASTM F2179-20 Sec. 4.2 (Mod) / ASTM C149	Shall not crack or break after tested per below - prepare a cold-water bath at 21± 1.1°C (70 ± 2°F). - prepare a hot bath at 71 ± 1.1°C (160 ± 2°F) - immerse the sample completely in the hot water bath and allow to soak for 5 min + 10 s. - transfer the sample to the cold bath, and immerse for at least 30 s. - remove the sample from the cold bath and examine the sample for any cracking. Note: - the hot water that collects within the container during the first immersion shall be retained in the container through the second immersion - the time of transfer from the hot bath to the cold bath shall be 15 ± 1 s Modification: sampling procedure not followed and expanded scope to all other glass products in addition to candle containers.	Id	PASS

REMARK:

1. No enclosed protocol for test results in this report.

□□□□□□ □□□□□□□ □□□□□□□□ □□□□□□□ □□□□□□□ □□□□□□ □□□□ □□ □□□□□ □□□□□ □□□ □□ □□□ □□ □□□□□□ □□□ □□□□□ □□□ □□□□□□□□ □

.



□□□□□□ □□□□□□ □□□□□

□□□□□ Cupwind □□□□ □□□□□□ □□□□□□ □□ □□□□ □□□.

□□ □□□□ 144 / □□□□ 72 / □□□□ 48 / □□□□ 24 □□□□□ □□□ □ □□□□□ □□□□□□□□ □□□□ □□□□ □□□□ □□ □□□□□ □□□ □□□ □□□□□ □□ □□□□□□ □□□□□.

[illegible].

Wick Trimmer Cutter
Zinc Alloy Lid
Wooden Lid
Neck
Stopper
Reed
Gift Box.
Cupwind
Gift Box

[illegible]

[illegible] Cupwind [illegible].