



Cupwind
 70 6000



Cupwind 48



TEST REPORT

SHENZHEN JIERUIMA TRADING CO., LTD
NO.415 RUNLIAN BUILDINGS, SHENZHU ROAD,
HENGANG, 518115, SHENZHEN, CHINA

LAB LOCATION: SHENZHEN
LAB NUMBER: (8521)097-0435

ATTN: EMMA ZOU
CC: emma@cupwind.com

DATE IN: APR 07, 2021
MOD. LOG IN: /
DATE OUT: APR 13, 2021
REVISED DATE: /
WORKING DAYS: 5
PAGE: 2 OF 4

| OVERALL RATING | |
|----------------|---|
| PASS | X |
| FAIL | |
| DATA | |

TESTING FOR
CA 65 LEAD & CADMIUM ON NON-FOOD/
BEVERAGE GLASSWARE-EXTERIOR

| | | | |
|----------------------|-------------------------------|---|--|
| Sample Description: | IRIDESCENT COATING CANDLE JAR | | |
| Manufacturer: | CUPWIND COOPERATED | P.O. No.: | / |
| Buyer: | IPSY | Style: | / |
| Country of Origin: | CHINA | Country of Destination: | USA |
| Color: | IRIDESCENT | SKU Number: | ITEM#: 8090 |
| Brand name: | CUPWIND® | | |
| Re-test: | Yes: <input type="checkbox"/> | No: <input checked="" type="checkbox"/> | Charge Vendor: Yes: <input checked="" type="checkbox"/> No: <input type="checkbox"/> |
| Previous Report No.: | / | | |

EXECUTIVE SUMMARY:

| Test content | Result/Rating |
|--|---------------|
| CA 65 Lead & Cadmium on non-food/beverage glassware-exterior | Meet/Pass |

| Effectiveness of annealing | ASTM F2179-20 Sec. 4.2 (Mod) | With a tungsten carbide scribe, scratch once around the inside knuckle of the article. Then scratch an "X" across the entire inside bottom surface of the article. All scratches are to be made using sufficient pressure to just penetrate the surface of the glass. Fill each article with water at the same room temperature as the glass. Wait 15 minutes, then empty the water and examine each piece for fractures. Shall show no fractures. Report the number of fractures, if any, for each test. Modification: expanded scope to all other glass products in addition to candle containers. | M | PASS |
|----------------------------|--|---|---|------|
| Thermal shock | ASTM F2179-20 Sec. 4.2 (Mod) / ASTM C149 | Shall not crack or break after tested per below - prepare a cold-water bath at 21±1.1°C (70±2°F). - prepare a hot bath at 71±1.1°C (160±2°F) - immerse the sample completely in the hot water bath and allow to soak for 5 min ± 10 s. - transfer the sample to the cold bath, and immerse for at least 30 s. - remove the sample from the cold bath and examine the sample for any cracking. Note: - the hot water that collects within the container during the first immersion shall be retained in the container through the second immersion - the time of transfer from the hot bath to the cold bath shall be 15 ± 1 s Modification: sampling procedure not followed and expanded scope to all other glass products in addition to candle containers. | M | PASS |

REMARK:

- No enclosed protocol for test results in this report.

0000000000 .0000 000 000 00 0000000 00000 00000 000000000 0000000 000000 00000000 0000
 0000000000 0000000000 0000000000 0000000000 0000 00000000 00000000 00000000 00000000 00000000
 000000000000 00000000 000000000000.

Cali 65 Pro