

Barattoli di candele iridescenti all'ingrosso blu 8 once



La nostra forza:

Laboratorio di decorazione di 10000 mq.

20 tipi di diverse macchine per decorare.

20 anni di esperienza nel settore della decorazione.

Supporto di oltre 20 fabbriche di vetro stabili.

Marchi famosi in tutto il mondo come Armani Zara ecc.

Cupwind è [vendita all'ingrosso di vasetti di candele iridescenti in Cina](#) da più di 10 anni.



Caoting iridescente all'esterno, spruzzi blu all'interno

rivestimento stabile che può superare il test del nastro a tratteggio incrociato M616

MOQ 2000 pezzi sul rivestimento iridescente

Look di lusso che è il nuovo trend del mercato



Cupwind offre anche accessori portacandele, come [set di strumenti per candele](#) compreso il tagliastoppino, lo sniffatore di stoppino, [portacandele](#), coperchi per barattoli di candele come coperchi in acciaio inox, coperchi in legno, coperchi in bambù con guarnizione.



Wick Trimmer Cutter



Zinc Alloy Lid



Wooden Lid



Neck



Stopper



Reed



Gift Box.



Gift Box

Tutti i [porta candele](#) i prodotti che spediamo sono testati superati da terzi, i test che di solito procediamo come ricottura e shock termico, piombo e cadmio.



TEST REPORT

SHENZHEN JIERUIMA TRADING CO., LTD
NO.415 RUNLIAN BUILDING, SHENZHU ROAD,
HENGGAO, 518115, SHENZHEN, CHINA

LAB LOCATION: SHENZHEN
LAB NUMBER: (8521)097-0435

ATTN: EMMA ZOU
CC: emma@cupwind.com

DATE IN: APR 07, 2021
MOD. LOG IN:
DATE OUT: APR 13, 2021
REVISED DATE:
WORKING DAYS: 5
PAGE: 2 OF 4

OVERALL RATING

PASS	X
FAIL	
DATA	

TESTING FOR CA 65 LEAD & CADMIUM ON NON-FOOD/ BEVERAGE GLASSWARE-EXTERIOR

Sample Description:	IRIDESCENT COATING CANDLE JAR
Manufacturer:	CUPWIND COOPERATED
Facility:	IPSY
Buyer:	Style: /
Country of Origin:	CHINA
Country of Destination:	USA
Color:	IRIDESCENT
SKU Number:	ITEM#: 8090
Brand name:	CUPWIND®
Re-test:	Yes: ☐ No: ☒
Charge Vendor:	Yes: ☒ No: ☐
Previous Report No.:	/



(8521)097-0435
Page 3 of 4

EXECUTIVE SUMMARY:

Test content	Result Rating	
CA 65 Lead & Cadmium on non-food beverage glassware-exterior	Meets/Pass	
Effectiveness of annealing	ASTM F2175-20 Sec. 4.2 (Mod)	M PASS
	With a tungsten carbide scribe, scratch once around the inside knuckle of the article. Then scratch an "X" across the entire inside bottom surface of the article. All scratches are to be made using sufficient pressure to just penetrate the surface of the glass. Fill each article with water at the same room temperature as the glass. Wait 15 minutes, then empty the water and examine each piece for fractures. Shall show no fractures. Report the number of fractures, if any, for each test. Modification: expanded scope to all other glass products in addition to candle containers.	
Thermal shock	ASTM F2175-20 Sec. 4.2 (Mod) / ASTM C149	M PASS
	Shall not crack or break after tested per below: - prepare a cold-water bath at 21± 1.1°C (70 ± 2°F). - prepare a hot bath at 71 ± 1.1°C (160 ± 2°F) - immerse the sample completely in the hot water bath and allow to soak for 5 min ± 10 s. - transfer the sample to the cold bath, and immerse for at least 30 s. - remove the sample from the cold bath and examine the sample for any cracking. Note: - the hot water that collects within the container during the first immersion shall be retained in the container through the second immersion. - the time of transfer from the hot bath to the cold bath shall be 15 ± 1 s. Modification: sampling procedure not followed and expanded scope to all other glass products in addition to candle containers.	

REMARK:

- No enclosed protocol for test results in this report.

Cupwind sa come proteggere ogni pezzo di prodotto, avvolgiamo ogni bicchiere con un sacchetto di plastica per evitare la polvere, ogni barattolo di candela è separato da divisori per uova dallo sfregamento a vicenda, è preferibile un pallet di legno durante il trasporto,

alla fine, noi aggiungere una rete di cotone in corrispondenza della porta del contenitore per evitare che i cartoni cadano.

