



230ml 65 10 14



Cupwind□□□□□□□□□□□□□□□□□□□□ □



TEST REPORT

SHENZHEN JIERUMA TRADING CO., LTD
NO.415 RUNLIAN BUILDING, SHENZHU ROAD
HONGKANG, 518115, SHENZHEN, CHINA

LAB LOCATION: SHENZHEN
LAB NUMBER: (852) 3087-6435

ATTN: EMMA ZOU
CC: emma@cupwind.com

DATE IN: APR 07, 2021
MOD. LOG IN: /
DATE OUT: APR 13, 2021
REVISED DATE: /
WORKING DAYS: 5
PAGE: 2 OF 4

OVERALL RATING	
PASS	<u>X</u>
FAIL	<u> </u>
DATA	<u> </u>

TESTING FOR
CA 65 LEAD & CADMIUM ON NON-FOOD /
BEVERAGE GLASSWARE-EXTERIOR


Sample Description:		DESCENDANT COATING CANDLE JAR	
Manufacturer:	CUPWIND COOPERATED FACILITY	P.O. No.:	/
Buyer:	PRV	Style:	
Country of Origin:	CHINA	Country of Destination:	USA
Commodity:	DESCENDANT	SKU Number:	11044-0090
Brand Name:	CUPWIND®		
Re-test:	Yes: ☐ No: ☐	Change Vendor:	Yes: ☐ No: ☐
Previous Report No.:	/		

EXECUTIVE SUMMARY:

Test content		Result Rating		
CA 101 Lead & Cadmium on non-food/overage glassware interior		Moist Heat		
Effectiveness of annealing	ASTM F2179-96 Sec. 4.2 (NAI)	With a tungsten-carbide wire, scratch twice around the inside rim of the article. Then scribe an "X" across the inside bottom surface of the article. All scratches are to be made using sufficient pressure to just penetrate the surface of the glass. Fill article with water at the same room temperature as the glass. Wait 15 minutes. Remove the water and examine each piece for fractures. Each article is to fracture. Report the number of fractures, if any, for each test.	M	PA33
Thermal shock	ASTM F2179-96 Sec. 4.2 (M2) A312M (14)	Modification: expanded scope to all other glass products in addition to landfill containers. Soak test sample in hot water (180 ± 10 °F) for 2 minutes. Prepare a cold-water bath at 21 ± 1 °C (70 ± 2 °F). Prepare a hot bath at 21 ± 1 °C (70 ± 2 °F) and immerse the sample completely for 12 ± 1 minutes. Transfer the sample to the cold bath and immerse for at least 30 s. Remove the sample from the cold bath and examine the sample for any cracking. Note: - the hot water that collects within the container during the first immersion shall be retained in the container - the subsequent immersion - the time of transfer from the hot bath to the cold bath shall be 15 ± 1 s Modification: sampling procedure not followed and expanded scope to all other glass products in addition to landfill containers.	M	PA33

REMARK.

1. Not reviewed/protocol for test results in this report.

[illegible]

24 / 48 / 72 / 144 opp

[illegible]



Cupwind