



Cupwind OEM / ODM



Wick Trimmer Cutter



Zinc Alloy Lid



Wooden Lid



TEST REPORT



8821097 048
Page 3 of 4

Call 65 Pro ASTM

ATTN: EMMA ZOU
DATE OUT: 2024-11-20
REVISED DATE: /
WORKING DAYS: 5
PAGE: 2 OF 4

Method	Standard	Result	Pass	Fail
Chemical analysis of annealing	ASTM F2195-20 Sec. 4.2 (NA6)	Nil on non-food/beverage glassware exterior	Result: Pass	
Normal shock	ASTM F2195-20 Sec. 4.2 (NA6) / ASTM C149	Modification: expanded scope to all other glass products in addition to candle containers. Shall not crack or break after tested per below: - prepare a cold-water bath at 21 ± 1 °C (70 ± 2 °F); - prepare a hot bath at 71 ± 1 °C (160 ± 2 °F); - immerse the sample completely in the hot water bath and allow to soak for 5 min ± 15 s; - transfer the sample to the cold bath and immerse for at least 30 s; - remove the sample from the cold bath and examine the sample for any cracking. Note: - the hot water that collects within the container during the first immersion shall be retained in the container through the second immersion. - the time of transfer from the hot bath to the cold bath shall be 15 ± 1 s. Modification: sampling procedure not followed and expanded scope to all other glass products in addition to candle containers.	Result: Pass	

OVERALL RATING	
PASS	X
FAIL	
DATA	

TESTING FOR CA 65 LEAD & CADMIUM ON NON-FOOD BEVERAGE GLASSWARE-EXTERIOR

Sample Description: IRRIDESCENT COATING CANDLE JAR

Color: IRIDESCENT

Country of Origin: CHINA

Country of Destination: USA

Brand name: CUPWIND 8

SKU Number: ITEM# 8090

Re-test: Yes: No:

Change Vendor: Yes: No:

Previous Report No.: 17

REMARK:
1. No enclosed protocol for test results in this report.

20

20

20

□□□□□□□□□□□□□□□□

