

15oz kolorowy szklany świecznik ręcznie robiony



Szkło jest ręcznie robione z bardzo luksusowym wyglądem, nadaje się do wypełnienia woskiem 15 uncji. Ten [szklany świecznik](#) jest wykonany z mieszanego kolorowego szkła sodowo-wapniowego. Ciężki, gruby i wytrzymały, idealny do promocji premium.



[Ręcznie robiony kolorowy świecznik](#) nie jest w stanie sprawić, by każdy kieliszek był dokładnie taki sam. Każda szklanka może więc wyglądać nieco inaczej niż druga. Ale to nie umniejsza żadnej fantazji świecznika.



Mamy pasującą drewnianą pokrywę do tego 15 uncji [świecznik](#). Materiał drewna jest dostępny w płytach MDF, sosna, bambus, buk, orzech, paulownia, akacja, drewno gumowe, dąb czerwony, dąb biały, jesion europejski, klon itp.



Cupwind to [Dostawca świeczników ze szkła kolorowego w Chinach](#), akceptujemy niestandardowy projekt OEM/ODM i możemy stworzyć własny kształt z/bez nazwy marki. Dekoracja dostępna do natryskiwania, galwanizacji, malowania metalicznego, kalkomanii, tłoczenia na gorąco, sitodruku, piaskowania, transferu wody itp.



Wick Trimmer Cutter



Zinc Alloy Lid



Wooden Lid



Neck



Stopper



Reed




Gift Box.



Gift Box

Jest więcej **akcesoria do świec** możemy dostarczyć oprócz drewnianych pokrywek. Na życzenie możemy sprzedać gotowe produkty ze świecami i pudełkami prezentowymi.



Owijamy każdy szklany świecznik torbą opp, aby chronić przed kurzem, a następnie kartony z tektury falistej z przegrodami poprzecznymi. Palety drewniane zawsze sprawdzą się w przypadku przesyłek LCL, a w miejscu drzwi dodamy bawełnianą siatkę, aby zabezpieczyć przed upadkiem podczas otwierania drzwi kontenera.



TEST REPORT



(8521)097-0435
Page 3 of 4

SHENZHEN JIERUIMA TRADING CO., LTD
NO.415 RUNLIAN BUILDING, SHENZHU ROAD,
HENGANG, 518115, SHENZHEN, CHINA

LAB LOCATION: SHENZHEN
LAB NUMBER: (8521)097-0435

ATTN: EMMA ZOU
CC: emma@cupwind.com

DATE IN: APR 07, 2021
MOD. LOG IN: /
DATE OUT: APR 13, 2021
REVISED DATE: /
WORKING DAYS: 5
PAGE: 2 OF 4

OVERALL RATING

PASS ☒
FAIL ☐
DATA ☐

TESTING FOR
CA 65 LEAD & CADMIUM ON NON-FOOD /
BEVERAGE GLASSWARE-EXTERIOR

Sample Description:	IRIDESCENT COATING CANDLE JAR		
Manufacturer:	CUPWIND COOPERATED FACILITY	P.O. No.:	/
Buyer:	IPSY	Style:	/
Country of Origin:	CHINA	Country of Destination:	USA
Color:	IRIDESCENT	SKU Number:	ITEM#: 8090
Brand name:	CUPWIND®		
Re-test:	Yes: ☐ No: ☒	Charge Vendor:	Yes: ☒ No: ☐
Previous Report No.:	/		

EXECUTIVE SUMMARY:

Test content		Result/Rating		
CA 65 Lead & Cadmium on non-food/beverage glassware-exterior		Meet/Pass		
Effectiveness of annealing	ASTM F2179-20 Sec. 4.2 (Mod)	With a tungsten carbide scribe, scratch once around the inside knuckle of the article. Then scratch an "X" across the entire inside bottom surface of the article. All scratches are to be made using sufficient pressure to just penetrate the surface of the glass. Fill each article with water at the same room temperature as the glass. Wait 15 minutes, then empty the water and examine each piece for fractures. Shall show no fractures. Report the number of fractures, if any, for each test. Modification: expanded scope to all other glass products in addition to candle containers.	M	PASS
Thermal shock	ASTM F2179-20 Sec. 4.2 (Mod) / ASTM C149	Shall not crack or break after tested per below - prepare a cold-water bath at 21±1.1°C (70 ± 2°F) - prepare a hot bath at 71 ±1.1°C (160 ± 2°F) - immerse the sample completely in the hot water bath and allow to soak for 5 min ± 10 s. - transfer the sample to the cold bath, and immerse for at least 30 s, - remove the sample from the cold bath and examine the sample for any cracking. Note: - the hot water that collects within the container during the first immersion shall be retained in the container through the second immersion - the time of transfer from the hot bath to the cold bath shall be 15 ± 1 s Modification: sampling procedure not followed and expanded scope to all other glass products in addition to candle containers.	M	PASS

REMARK:

1. No enclosed protocol for test results in this report.

Wszystkie nasze szklane słoiki na świece są testowane przez stronę trzecią. Zwykle stosujemy testy Cali 65 Pro, testy ASTM (wyżarzanie i szok termiczny), testy ołowiu i kadmu.