

Hurtownia satynowych słoików na świece 3,15 x 3,5 cala



To pięknie [świecznik](#) jest ozdobiony kolorowymi sprayami, podobnymi do satyn. niepowtarzalny wygląd wyróżnia ją na rynku i przyciąga wzrok.



Satynowe spraye można również ozdobić [butelki z dyfuzorem](#), flakony perfum, kosmetyki i ciała, no cóż, Cupwind robi te dekoracje we własnym warsztacie, który ma 10000m² z ponad 20 różnymi maszynami, aby uzyskać bogate efekty na [.](#)



Co więcej, Cupwind od lat oferuje akcesoria do świec, takie jak metalowe wieczka, pudełka na prezenty, [narzędzie do pielęgnacji świec](#), kołnierze, zatyczka itp.



Wick Trimmer Cutter



Zinc Alloy Lid



Wooden Lid



Neck



Stopper



Reed




Gift Box.



Gift Box

Cupwind dba o każdy kawałek [puste słoiki na świece](#) z bezpieczeństwem. Każda szklanka była owinięta torebką opp, aby uniknąć kurzu, owadów, a następnie niektóre kawałki zostały umieszczone w skrzynce eksportowej z przegródkami na jajka.



Ostatnie, ale nie najmniej ważne, wszystkie [szklane słoiki na świece](#) są testowane przez strony trzecie, testy, które zawsze przeprowadzamy, są takie jak test wyżarzania i szoku termicznego, test FDA, test kreskowania krzyżowego.



TEST REPORT

SHEZHEN JIERUIMA TRADING CO., LTD
NO.415 RUNLIAN BUILDING, SHENZHU ROAD,
HENGANG, 518115, SHENZHEN, CHINA

LAB LOCATION: SHENZHEN
LAB NUMBER: (8521)097-0435

ATTN: EMMA ZOU
CC: emma@cupwind.com

DATE IN: APR 07, 2021
MOD. LOG IN: /
DATE OUT: APR 13, 2021
REVISED DATE: /
WORKING DAYS: 5
PAGE: 2 OF 4

OVERALL RATING

PASS ☒ X
FAIL ☐
DATA ☐

TESTING FOR CA 65 LEAD & CADMIUM ON NON-FOOD / BEVERAGE GLASSWARE-EXTERIOR

Sample Description:	IRIDESCENT COATING CANDLE JAR		
Manufacturer:	CUPWIND COOPERATED FACILITY	P.O. No.:	/
Buyer:	IPSY	Style:	/
Country of Origin:	CHINA	Country of Destination:	USA
Color:	IRIDESCENT	SKU Number:	ITEM# 8090
Brand name:	CUPWIND'S		
Re-test:	Yes: ☐ No: ☒ X	Charge Vendor:	Yes: ☒ X No: ☐
Previous Report No.:	/		



(8521)097-0435
Page 3 of 4

EXECUTIVE SUMMARY:

Test content	Result Rating
CA 65 Lead & Cadmium on non-food beverage glassware-exterior	Meet/Pass
Effectiveness of annealing	ASTM F2175-20 Sec. 4.2 (Mod) M PASS With a tungsten carbide scribe, scratch once around the inside knuckle of the article. Then scratch an "X" across the entire inside bottom surface of the article. All scratches are to be made using sufficient pressure to just penetrate the surface of the glass. Fill each article with water at the same room temperature as the glass. Wait 15 minutes, then empty the water and examine each piece for fractures. Shall show no fractures. Report the number of fractures, if any, for each test. Modification: expanded scope to all other glass products in addition to candle containers.
Thermal shock	ASTM F2175-20 Sec. 4.2 (Mod) / ASTM C149 M PASS Shall not crack or break after tested per below: - prepare a cold-water bath at 21±1.1°C (70±2°F) - prepare a hot bath at 71±1.1°C (160±2°F) - immerse the sample completely in the hot water bath and allow to soak for 5 min ± 10 s. - transfer the sample to the cold bath, and immerse for at least 30 s. - remove the sample from the cold bath and examine the sample for any cracking. Note: - the hot water that collects within the container during the first immersion shall be retained in the container through the second immersion - the time of transfer from the hot bath to the cold bath shall be 15 ± 1 s Modification: sampling procedure not followed and expanded scope to all other glass products in addition to candle containers.

REMARK:

1. No enclosed protocol for test results in this report.