

Handcraft Watercolor 200ml Glass Diffuser Bottle Reed



This diffuser bottle glass hold 200ml fragrance oil. The watercolor pattern is handmade and exclusive in CUPWIND. We are leading [china 200ml glass diffuser bottle factory](#).

The diffuser glass is able to spray different pantone colors which makes it match well with different designs candle glass and fragrance scents. It's perfect for home decor,

aromatherapy, spa, meditation, bathroom.



This diffuser with handmade watercolor design, there is matching candles design for it. It's very good matching home decor product for customers. The empty glass diffuser bottle is also a good vase for flowers, simple and classic.



Cupwind is one of the most professional [China 200ml glass diffuser bottle manufacturer](#). We have our own decorating workshop to keep an eye on the quality of the reed diffuser bottle before it's shipped out.











Cupwind also offers other accessories that are related to the reed diffuser bottle such as reed, plug, gift box, stopper etc.

We have 6 stable cooperative partners for years. The quality is great match with our candle holders.



Accessories That Related

With requests of our customers, Cupwind also offers accessories such as gift box for scented candles, wick tool set like wick trimmer, cutter, snuffer, lids in wood and metal like stainless steel and zinc alloy.



Zinc Alloy Lid

Wick Trimmer Cutter



Wooden Lid

Tin metal lid



Glass Lid

Stopper



Neck

Reed



Gift Box

Gift Box



We also offer gift box OEM and ODM for reed diffuser bottles. If gift box is not necessary, the common way we are using is to wrap each glass diffuser bottle by an opp bag to keep away from dust, corrugated cartons with cross board dividers. Wooden pallet is always efficient while in transportation, and we will add a cotton net in the door place to protect from falling when opening the container door.



All of our glass orders are tested by a third party. Usually we go with Cali 65 Pro tests, ASTM (Annealing and Thermal Shock) tests, Lead and Cadmium tests.



TEST REPORT



(8521)097-0435
Page 3 of 4

SHENZHEN JIERUIMA TRADING CO., LTD
NO.415 RUNLIAN BUILDING, SHENZHU ROAD,
HENGANG, 518115, SHENZHEN, CHINA

LAB LOCATION: SHENZHEN
LAB NUMBER: (8521)097-0435

ATTN: EMMA ZOU
CC: emma@cupwind.com

DATE IN: APR 07, 2021
MOD. LOG IN: /
DATE OUT: APR 13, 2021
REVISED DATE: /
WORKING DAYS: 5
PAGE: 2 OF 4

OVERALL RATING	
PASS	X
FAIL	
DATA	

TESTING FOR
CA 65 LEAD & CADMIUM ON NON-FOOD /
BEVERAGE GLASSWARE-EXTERIOR

Sample Description:	IRIDESCENT COATING CANDLE JAR		
Manufacturer:	CUPWIND COOPERATED	P.O. No.:	/
Buyer:	IPSY	Style:	/
Country of Origin:	CHINA	Country of Destination:	USA
Color:	IRIDESCENT	SKU Number:	ITEM# 8090
Brand name:	CUPWIND®		
Re-test:	Yes: <input type="checkbox"/>	No: <input checked="" type="checkbox"/>	Charge Vendor: Yes: <input type="checkbox"/> No: <input type="checkbox"/>
Previous Report No.:	/		

EXECUTIVE SUMMARY:

Test content		Result/Rating
CA 65 Lead & Cadmium on non-food/beverage glassware-exterior		Meet/Pass
Effectiveness of annealing	ASTM F2179-20 Sec. 4.2 (Mod)	M PASS
	<p>With a tungsten carbide scribe, scratch once around the inside knuckle of the article. Then scratch an "X" across the entire inside bottom surface of the article. All scratches are to be made using sufficient pressure to just penetrate the surface of the glass. Fill each article with water at the same room temperature as the glass. Wait 15 minutes, then empty the water and examine each piece for fractures. Shall show no fractures. Report the number of fractures, if any, for each test.</p> <p>Modification: expanded scope to all other glass products in addition to candle containers.</p>	
Thermal shock	ASTM F2179-20 Sec. 4.2 (Mod) / ASTM C149	M PASS
	<p>Shall not crack or break after tested per below</p> <ul style="list-style-type: none">- prepare a cold-water bath at $21 \pm 1.1^{\circ}\text{C}$ ($70 \pm 2^{\circ}\text{F}$).- prepare a hot bath at $71 \pm 1.1^{\circ}\text{C}$ ($160 \pm 2^{\circ}\text{F}$).- immerse the sample completely in the hot water bath and allow to soak for $5 \text{ min} \pm 10 \text{ s}$.- transfer the sample to the cold bath, and immerse for at least 30 s.- remove the sample from the cold bath and examine the sample for any cracking. <p>Note:</p> <ul style="list-style-type: none">- the hot water that collects within the container during the first immersion shall be retained in the container through the second immersion- the time of transfer from the hot bath to the cold bath shall be $15 \pm 1 \text{ s}$ <p>Modification: sampling procedure not followed and expanded scope to all other glass products in addition to candle containers.</p>	

REMARK:

1. No enclosed protocol for test results in this report.