

**Бутылка отражателя элегантного домашнего благоухания
керамическая с крышкой цветка**



Cupwind опытный [Китай поставщик керамических диффузоров](#), мы поставляем бутылки диффузора как из стеклянного материала, так и из керамического материала. Минимальный объем заказа для керамической бутылки с диффузором может составлять всего 2000 шт., различная форма, размер и крышки могут быть изготовлены по индивидуальному заказу.



Большой флакон с диффузором классической круглой формы вмещает 25 унций масляного аромата. Белая керамическая бутылка-диффузор округлой формы с узором в виде поперечных полос идеально подходит для украшения помещения.



В виде [Фабрика керамических диффузоров в Китае](#), Surwind всегда будет предлагать модные и специальные продукты, чтобы сделать ваш бренд уникальным. Для этой бутылки с диффузором у нас есть крышка с цветком, мы можем настроить цвет и размер по вашему желанию.



Wick Trimmer Cutter



Zinc Alloy Lid



Wooden Lid



Neck



Stopper



Reed





Gift Box.



Gift Box

Кроме керамической крышки, мы также поставляем другие аксессуары для бутылок с диффузором, такие как пробка, заглушка, трость, подарочная коробка и т. д.



Мы заворачиваем каждый продукт в полипропиленовый пакет для защиты от пыли, а затем в гофрированные коробки с поперечными разделителями. Деревянные поддоны всегда эффективны для перевозки LCL, и мы добавим хлопчатобумажную сетку в месте двери, чтобы защитить от падения при открытии двери контейнера..



TEST REPORT



(8521)097-0435
Page 3 of 4

SHENZHEN JIERUIMA TRADING CO., LTD
NO.415 RUNLIAN BUILDING, SHENZHU ROAD,
HENG GANG, 518115, SHENZHEN, CHINA

LAB LOCATION: SHENZHEN
LAB NUMBER: (8521)097-0435

ATTN: EMMA ZOU
CC: emma@cupwind.com

DATE IN: APR 07, 2021
MOD. LOG IN: /
DATE OUT: APR 13, 2021
REVISED DATE: /
WORKING DAYS: 5
PAGE: 2 OF 4

OVERALL RATING

PASS ☒ X
FAIL ☐
DATA ☐

TESTING FOR CA 65 LEAD & CADMIUM ON NON-FOOD / BEVERAGE GLASSWARE-EXTERIOR

Sample Description:	IRIDESCENT COATING CANDLE JAR		
Manufacturer:	CUPWIND COOPERATED FACILITY	P.O. No.:	/
Buyer:	IPSY	Style:	/
Country of Origin:	CHINA	Country of Destination:	USA
Color:	IRIDESCENT	SKU Number:	ITEM# 8090
Brand name:	CUPWIND®		
Re-test:	Yes: ☐ No: ☒ X	Charge Vendor:	Yes: ☒ X No: ☐
Previous Report No.:	/		

EXECUTIVE SUMMARY:

Test content		Result Rating	
CA 65 Lead & Cadmium on non-food/beverage glassware-exterior		Meet/Pass	
Effectiveness of annealing	ASTM F2179-20 Sec. 4.2 (Mod)	With a tungsten carbide scribe, scratch once around the inside knuckle of the article. Then scratch an "X" across the entire inside bottom surface of the article. All scratches are to be made using sufficient pressure to just penetrate the surface of the glass. Fill each article with water at the same room temperature as the glass. Wait 15 minutes, then empty the water and examine each piece for fractures. Shall show no fractures. Report the number of fractures, if any, for each test.	M PASS
Thermal shock	ASTM F2179-20 Sec. 4.2 (Mod) / ASTM C149	Modification: expanded scope to all other glass products in addition to candle containers. Shall not crack or break after tested per below - prepare a cold-water bath at $21 \pm 1.1^{\circ}\text{C}$ ($70 \pm 2^{\circ}\text{F}$). - prepare a hot bath at $71 \pm 1.1^{\circ}\text{C}$ ($160 \pm 2^{\circ}\text{F}$). - immerse the sample completely in the hot water bath and allow to soak for $5 \text{ min} \pm 10 \text{ s}$. - transfer the sample to the cold bath, and immerse for at least 30 s. - remove the sample from the cold bath and examine the sample for any cracking. Note: - the hot water that collects within the container during the first immersion shall be retained in the container through the second immersion - the time of transfer from the hot bath to the cold bath shall be $15 \pm 1 \text{ s}$. Modification: sampling procedure not followed and expanded scope to all other glass products in addition to candle containers.	M PASS

REMARK:

1. No enclosed protocol for test results in this report.

Все наши стеклянные банки для свечей тестируются третьей стороной. Обычно мы используем тесты Cali 65 Pro, тесты ASTM (отжиг и тепловой удар), тесты на свинец и кадмий.