Квадратный флакон с керамическим диффузором для дома, 6 унций

Cupwind опытный Китай керамический квадратный диффузор бутылка поставщик, мы поставляем флаконы-диффузоры как из стекла, так и из керамики. Минимальный объем заказа для керамической бутылки с диффузором может составлять всего 2000 шт., различная форма, размер и крышки могут быть изготовлены по индивидуальному заказу.

Флакон с диффузором классической квадратной формы, он содержит 6 унций масляного аромата, текстурная поверхность позволит вам испытать особое ощущение прикосновения, когда вы его держите. У нас есть подходящий керамический подсвечник, он станет прекрасным декоративным набором в ванной комнате.

В виде Китай квадратный керамический диффузор оптовик, Cupwind всегда будет предлагать модные и специальные продукты, чтобы сделать ваш бренд уникальным. Для этой бутылки с диффузором у нас есть крышка с цветком, мы можем настроить цвет и размер по вашему желанию.

Wick Trimmer Cutter

Zinc Alloy Lid

Wooden Lid

Neck

Stopper

Reed

Gift Box.

Gift Box

Кроме керамической крышки, мы также поставляем другие аксессуары для бутылок с диффузором, такие как пробка, заглушка, трость, подарочная коробка и т. д.


Cupwind
Cupwind®
Scented Candle


BRAND NAME
Cupwind

Мы заворачиваем каждый продукт в полипропиленовый пакет для защиты от пыли, а затем в гофрированные коробки с поперечными разделителями. Деревянные поддоны всегда эффективны для перевозки LCL, и мы добавим хлопчатобумажную сетку в месте двери, чтобы защитить от падения при открытии двери контейнера..



(8521)097-0435
Page 3 of 4

TEST REPORT

SHENZHEN JIERUIMA TRADING CO., LTD
NO.415 RUNLIAN BUILDING, SHENZHU ROAD,
HENGGANG, 518115, SHENZHEN, CHINA

LAB LOCATION: SHENZHEN
LAB NUMBER: (8521)097-0435

ATTN: EMMA ZOU
CC: emma@cupwind.com

DATE IN: APR 07, 2021
MOD. LOG IN: /
DATE OUT: APR 13, 2021
REVISED DATE: /
WORKING DAYS: 5
PAGE: 2 OF 4

OVERALL RATING	
PASS	X
FAIL	
DATA	

TESTING FOR
CA 65 LEAD & CADMIUM ON NON-FOOD / BEVERAGE GLASSWARE-EXTERIOR

Sample Description:	IRIDESCENT COATING CANDLE JAR		
Manufacturer:	CUPWIND COOPERATED FACILITY	P.O. No.:	/
Buyer:	IPSY	Style:	/
Country of Origin:	CHINA	Country of Destination:	USA
Color:	IRIDESCENT	SKU Number:	ITEM#: 8090
Brand name:	CUPWIND ®		
Re-test:	Yes: / No: X	Charge Vendor:	Yes: X / No:
Previous Report No.:	/		

EXECUTIVE SUMMARY:

Test consent	Result/Rating
CA 65 Lead & Cadmium on non-food/beverage glassware-exterior	Meet/Pass

Effectiveness of annealing	ASTM F2179-20 Sec. 4.2 (Mod)	With a tungsten carbide scribe, scratch once around the inside knuckle of the article. Then scratch an "X" across the entire inside bottom surface of the article. All scratches are to be made using sufficient pressure to just penetrate the surface of the glass. Fill each article with water at the same room temperature as the glass. Wait 15 minutes, then empty the water and examine each piece for fractures. Shall show no fractures. Report the number of fractures, if any, for each test. Modification: expanded scope to all other glass products in addition to candle containers.	M	PASS
Thermal shock	ASTM F2179-20 Sec. 4.2 (Mod) / ASTM C149	Shall not crack or break after tested per below - prepare a cold-water bath at 21± 1.1°C (70 ± 2°F), - prepare a hot bath at 71 ± 1.1°C (160 ± 2°F) - immerse the sample completely in the hot water bath and allow to soak for 5 min ± 10 s. - transfer the sample to the cold bath, and immerse for at least 30 s, - remove the sample from the cold bath and examine the sample for any cracking. Note: - the hot water that collects within the container during the first immersion shall be retained in the container through the second immersion - the time of transfer from the hot bath to the cold bath shall be 15 ± 1 s Modification: sampling procedure not followed and expanded scope to all other glass products in addition to candle containers.	M	PASS

REMARK:

1. No enclosed protocol for test results in this report.

Все наши стеклянные банки для свечей тестируются третьей стороной. Обычно мы используем тесты Cali 65 Pro, тесты ASTM (отжиг и тепловой удар), тесты на свинец и кадмий.